

Specification of Bitumen Penetration 30/45

Bitumen 30/45	Test method	Unit	Specification
Penetration @ 25°C	IP 49	mm/10	30/45
Softening point °C	IP 58	°C	52/60
Resistance to hardening at 163°C			
Change of mass		%	0.5
Retained penetration	IP 49	%	53 min
Softening point after hardening	IP 58	°C	54
Flashpoint °C	IP 36	°C	240 min
Solubility	IP 47	wt %	99 min
Kinematic Viscosity @ 135°C	IP 319	mm ² /s	400 min



No303,Navab Complex,Navab St,
Isfahan,Iran



www.rahabitumen.com



+983132355214



info@rahabitumen.com