

Specification of Bitumen Penetration 50/70

Bitumen 50/70	Test method	Unit	Specification
Penetration @ 25°C	IP 49	mm/10	50/70
Softening point °C	IP 58	°C	46/54
Resistance to hardening at 163°C			
Change of mass		%	0.5
Retained penetration	IP 49	%	50 min
Softening point after hardening	IP 58	°C	58
Flashpoint °C	IP 36	°C	230 min
Solubility	IP 47	wt %	99 min
Kinematic Viscosity @ 135°C	IP 370	mm ² /s	295 min



No303,Navab Complex,Navab St,
Isfahan,Iran



www.rahabitumen.com



+983132355214



info@rahabitumen.com