

Specification of oxidized bitumen 90/10

Bitumen 90/10	Test method	Unit	Specification
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°c	ASTM D5	mm/10	5/15
Softening point °c	ASTM D36	°C	85/95
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint c	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	Wt. %	99.5 max
Stop test	A.A.S.H.O.T102	---	negative



No303,Navab Complex,Navab St,
Isfahan,Iran



www.rahabitumen.com



+983132355214



info@rahabitumen.com