

# Specification of Bitumen (Asphalt) Emulsion CRS-2

Type: **Rapid-Setting**

Grade: **Cationic**

Standard: **ASTM D 2397M -13**

Property	Min	Max	Test Method
<b>Test on Emulsions</b>			
Viscosity, Saybolt Furol at 25 °C, SFS	100	400	ASTM D244
Storage stability test, 24-h, %	—	1	ASTM D6930
Demulsibility, 35 mL, 0.8 % dioctyl sodium sulfosuccinate, %	40	—	ASTM D6936
Particle charge test	Positive		ASTM D244
Sieve test, %	—	0.1	ASTM D6933
<b>Distillation:</b>			
Oil distillate, by volume of emulsion, %	—	3	ASTM D6997
Residue, %	65	—	ASTM D244
<b>Test on Residue from distillation test:</b>			
Penetration 77°F (25°C) 100g,5s mm	100	250	ASTM D5
Ductility 77°F (25°C) 5cm/min cm	40	—	ASTM D113
Solubility in trichloroethylene %	97.5	—	ASTM D2042



No303,Navab Complex,Navab St,  
Isfahan,Iran



[www.rahabitumen.com](http://www.rahabitumen.com)



+983132355214



[info@rahabitumen.com](mailto:info@rahabitumen.com)