

## **Product Data Sheet**

# 0.15% Pd 0.15% Pt/AS R45084

BASF DeOxo R45084 is used for the purification of  $CO_2$  or  $N_2$  in polyethylene terephthalate (PET) solid state polycondensation units.

#### General

DeOxo R 45084 is a catalyst in the form of spheres with a nominal diameter of 2.36 – 4 mm and with Palladium and Platinum as active components. The lower surface alumina carrier has been carefully chosen for providing optimum activity and high temperature stability.

#### **Product Application**

DeOxo R45084 is typically used for the combustion of ethylene glycol, acetaldehyde, dimer and light olefins coming from the solid-state polymerization of polyethylene terephthalate (PET).

Low levels of  $H_2$  will also be removed. The combustion products are  $CO_2$  and water vapor.

The different combustion reactions might be described as follows:

$$C_xH_yO_z + (x + y/4 - z/2) O_2 \rightarrow x CO_2 + y/2 H_2O (v)$$
 (1)  
 $H_2 + \frac{1}{2} O_2 \rightarrow H_2O (v)$   $(\Delta_R H) = -242 \text{ kJ/mol (2)}$ 

Due to the high exotherm of the indicated reactions, proper instrumentation and safety measures always need to be put in place to assure full control of the reaction.

Typical reaction temperatures are in the range of 150 – 550°C / 300 – 1 000°F. The maximum allowable temperature is 700°C / 1 300°F.

### **Special Operations**

Before unloading, the material should be oxidized.

## **Poisons**

As every Pd and Pt containing catalyst DeOxo R45084 is sensitive against Sulfur and its components. Heavy metals like As and Sb (as well as the compounds containing them), silicon compounds and oil mist from compressors can also have a detrimental effect on its performance.

#### **Storage**

DeOxo R45084 does not deteriorate or constitute any hazard when stored in sealed containers. The containers should not be allowed to become damp or wet and should not be stored in contact with organic or easily oxidizing vapors.

Target Properties	
Chemical Composition (dry basis)	0.15 % wt./wt. Pd and 0.15% Pt on special Alumina
Typical Physical Properties	
Packed Bulk Density, g/ml	0.66
Total Surface Area (BET), m <sup>2</sup> /g	90

<sup>\*</sup> These indicative properties do not represent process capabilities nor specifications

## **Packaging**

210 I steel drum with up to 100 kg net

#### **Points of Shipment**

Rome, Italy

#### **About Us**

BASF's Catalysts division is the world's leading supplier of environmental and process catalysts. The group offers exceptional expertise in the development of technologies that protect the air we breathe. produce the fuels that power our world and ensure efficient production of a wide variety of chemicals, plastics and other products, including advanced battery materials. By leveraging our industry-leading R&D platforms, passion for innovation and deep knowledge of precious and base metals, BASF's Catalysts division develops unique, proprietary solutions that drive customer success.

**BASF** - We create chemistry

#### **Americas**

BASF Corporation 25 Middlesex/Essex Turnpike Iselin, New Jersey, 08830, USA

Tel: +1-732-205-5000 Fax: +1-732-205-7725

Email: catalysts-americas@basf.com

#### **Asia Pacific**

BASF (China) Company Limited 300 Jiang Xin Sha Road, Pudong, Shanghai 200137 P.R. China

Tel: +86-21-2039 2549 Fax: +86-21-2039 4800-2549 Email: catalysts-asia@basf.com

### Europe, Middle East, Africa

BASF De Meern BV Catalysts The Netherlands Tel: +31-30-666 9437

Email: catalysts-europe@basf.com

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required. © 2015 BASF