

0.5% Pd/AS R4577

DeOxo DS

R4577 / DeOxo DS is used for the removal of hydrogen by reaction with oxygen (De-Oxo reaction).

General

R4577 / DeOxo DS is a catalyst in the form of spheres with a nominal diameter of 2 – 4.8 mm and with Palladium as active component. The higher surface alumina carrier has been carefully chosen for providing optimum activity. The material is delivered dry and pre-reduced.

Product Application

R4577 / DeOxo DS is used for the conversion of hydrogen in the presence of oxygen to form water (De-Oxo reaction) according to the following chemical formula:



This reaction can be applied in the production of pure hydrogen (e.g., as green hydrogen) or in the production of inert gases like N₂, He or Ar when adding hydrogen to remove oxygen. An alternative material for this application can be

0.3% Pd/AS R4578 (DeOxo DS3).

Typical reaction temperatures are in the range of 50 – 100°C / 120 – 210°F. The maximum allowable temperature is 500°C / 930°F.

Special Operations

R4577 / DeOxo DS might gain maximum activity via a short activation procedure. Before unloading, the material should be oxidized.

Poisons

As every Pd containing catalyst R4577 / DeOxo DS is sensitive against Sulfur and its components. Heavy metal containing compounds like AsH₃ can also have a determinantal effect on its performance. CO will have an impact on activity but might be compensated via higher temperature.

Storage

R4577 / DeOxo DS does not deteriorate or constitute any hazard when stored in sealed containers. The containers should not be allowed to become damp or wet and should not be stored in contact with organic or easily oxidizing vapors.

Target Properties*

Chemical Composition (dry basis)	0.5% wt./wt. Pd on special Alumina
---	------------------------------------

Typical Physical Properties

Packed Bulk Density, g/ml	Approx. 0.7
---------------------------	-------------

Total Surface Area (BET), m ² /g	Approx. 320
---	-------------

*These indicative properties do not represent process capabilities nor specifications

Packaging

- 120 l fiber drum with nominal up to 25 kg net
- 62 l fiber drum with nominal up to 40 kg net

Point of Shipment:

- Rome, Italy

About Us

BASF is a leading global manufacturer of catalysts for the chemical industry, with solutions across the chemical value chain. The business comprises chemical catalysts and adsorbents, refinery catalysts and custom catalysts. In the process catalysts business, priority is given to developing new and improved products that enable the chemical industry transformation to net-zero emissions.

The division's portfolio also includes battery materials and recycling solutions, as well as environmental catalysts and metal solutions. Customers from a variety of industries including Automotive & Transportation, Chemicals, Plastics or Energy & Resources benefit from our innovative solutions. Further information on BASF's Catalysts division is available on the Internet at www.catalysts.basf.com.

BASF - We create chemistry

Americas

BASF Corporation
Phone: +1-732-205-5000
Email: catalysts-america@basf.com

Asia Pacific

BASF (China) Company Limited
Phone: +86-21-2039 2549
Email: catalysts-asia@basf.com

Europe, Middle East, Africa

BASF Services Europe GmbH
Phone: +49-30-20055000
Email: catalysts-europe@basf.com

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required. © 2015 BASF

www.catalysts.basf.com/adsorbents