

Non-equilibrium Thermodynamic Foundation of the Grand-potential Phase Field Model

Jin Zhang ^{1,*}, James A. Warren,² and Peter W. Voorhees¹

¹*Department of Materials Science and Engineering,
Northwestern University, Evanston, IL 60208, USA*

²*Material Measurement Laboratory, National Institute of Standards and Technology,
100 Bureau Drive, Gaithersburg, 20899, MD, USA*

Choosing the correct free energy functional is critical when developing thermodynamically-consistent phase field models. We show that the grand-potential phase field model minimizes the Helmholtz free energy. While both functionals are at a minimum at equilibrium, the Helmholtz free energy decreases monotonically with time in the grand-potential phase field model, whereas the grand potential does not. Minimizing the grand potential implies a different problem where a system can exchange mass with its surroundings at every point, leading to a condition of iso-chemical-potential and invalidating mass conservation of the system.

The phase field method is widely used to describe the evolution of non-equilibrium systems. One of its most broad and successful applications is modeling the solidification of alloys. Early phase field models for alloys [1] do not decouple the bulk and interfacial energies, so they rely on a very thin interface (typically on the nanometer scale) to provide quantitative predictions. This imposes a significant computational constraint for practical applications of the models to systems ranging from micrometers to millimeters in size. The Kim-Kim-Suzuki (KKS) model [2] addressed this problem by viewing the interface as a two-phase mixture, allowing for a natural decoupling of the bulk and interfacial contributions, and permitting accurate predictions with significantly larger interface widths. However, to achieve this, a local equilibrium constraint must be fulfilled. This constraint, which involves the equality of the diffusion potentials for the two phases ($\tilde{\mu}^\alpha = \tilde{\mu}^\beta$), is a nonlinear equation for general free energies and must be solved at each grid point and each timestep, a computationally expensive undertaking. To avoid this, carefully crafted free energy densities can be used. Plapp [3] proposed a grand-potential formulation by switching from the concentration c to the diffusion potential $\tilde{\mu}$ as the natural variable. This treatment naturally fulfills the local equilibrium constraint and fully decouples the bulk and interfacial energies. This model has been extended to multiphase and multicomponent systems [4, 5] and is widely used for modeling alloy solidification and various other applications [6, 7].

Though not explicitly mentioned in the original paper [3], many researchers have leapt from the observation that the grand potential was used in Plapp’s approach to the conclusion that the grand-potential phase field model minimizes the system’s total grand potential [8–18]. Some researchers have pointed out that the evolution equations from the grand-potential phase field model do not appear to result from a variational derivation of the system’s total grand potential, but the point has not

been emphasized [7, 19, 20].

We show here that the grand-potential phase field model proposed by Plapp [3] actually minimizes the Helmholtz free energy under proper boundary conditions. Here, ‘minimize’ pertains to non-equilibrium thermodynamics: the free energy not only reaches an extremum at equilibrium, as described in classical thermodynamics, but also decreases monotonically with time (energy dissipation or the energy being a Lyapunov functional [21, 22]). Moreover, the concept of ‘equilibrium’ should be viewed as a state where all fast processes have happened while all slow processes have not, as highlighted by Feynman [23]. For example, solidification of an alloy can often be approximated as a process that takes place in *thermal equilibrium*, a state with rapid heat diffusion and slow mass diffusion. Thus, in the isothermal case, heat exchange is fast and temperature remains uniform while mass diffusion exists as a non-equilibrium process. The Helmholtz free energy decreases monotonically in this process. The case where the total grand potential is monotonically decreasing is related to the presence of *chemical equilibrium* at a timescale significantly longer than mass diffusion. An example analogous to isothermal is iso-chemical-potential (or iso- $\tilde{\mu}$), where mass exchange with the surroundings is fast to maintain the iso- $\tilde{\mu}$ condition, leading to the lack of mass conservation in the *system*. As Plapp uses mass conservation in his model, the system is not under an iso- $\tilde{\mu}$ condition, and the total grand potential does not decrease monotonically in time, despite the grand potential reaching its minimum at equilibrium (when mass diffusion is done). This observation in no way renders Plapp’s model incorrect, but this misapprehension could lead to substantive errors in interpreting the free energy functional and constructing thermodynamically-consistent phase field models.

Let us briefly review Plapp’s grand-potential phase field model [3]. The grand potential of a binary alloy system is defined as

$$\Omega[\phi, \tilde{\mu}] = \int_V \frac{1}{2} \kappa |\vec{\nabla} \phi|^2 + mg(\phi) + \omega(\phi, \tilde{\mu}) dV, \quad (1)$$

* jzhang@northwestern.edu

where ϕ is the phase field variable, $\tilde{\mu}$ is the diffusion potential, κ is the gradient coefficient, $g(\phi)$ is the double-well function, m is the height of the well, and the bulk grand-potential density is interpolated from the two phases

$$\omega = p(\phi)\omega^\alpha(\tilde{\mu}) + (1 - p(\phi))\omega^\beta(\tilde{\mu}), \quad (2)$$

where $p(\phi)$ is an interpolation function, and ω^α and ω^β are the grand-potential densities of each phase, which are both functions of the diffusion potential $\tilde{\mu}$.

The functional derivatives of the system's grand potential with respect to the two independent variables are

$$\frac{\delta\Omega}{\delta\phi} = -\kappa\vec{\nabla}^2\phi + mg'(\phi) + p'(\phi)(\omega^\alpha - \omega^\beta), \quad (3)$$

$$-\frac{\delta\Omega}{\delta\tilde{\mu}} = p(\phi)c^\alpha + (1 - p(\phi))c^\beta = c, \quad (4)$$

where c is the total concentration interpolated from the phase concentrations $c^\alpha = -\partial\omega^\alpha/\partial\tilde{\mu}$.

The evolution of the phase field variable ϕ follows the Allen-Cahn equation

$$\frac{\partial\phi}{\partial t} = -M_\phi \frac{\delta\Omega}{\delta\phi}, \quad (5)$$

where M_ϕ is the phase field mobility and is positive.

The evolution of the diffusion potential $\tilde{\mu}$ is derived from the mass conservation equation

$$\frac{\partial c}{\partial t} = -\vec{\nabla} \cdot \vec{J}, \quad (6)$$

where \vec{J} is the mass flux. In the grand-potential phase field model, Eq. 6 is reformulated to an evolution equation of the diffusion potential

$$\chi \frac{\partial\tilde{\mu}}{\partial t} = \vec{\nabla} \cdot (M\vec{\nabla}\tilde{\mu}) - p'(\phi)(c^\alpha - c^\beta) \frac{\partial\phi}{\partial t}, \quad (7)$$

where $\chi = \partial c/\partial\tilde{\mu}$ is the susceptibility, $p'(\phi) = dp/d\phi$, and we use

$$\vec{J} = -M\vec{\nabla}\tilde{\mu}, \quad (8)$$

where M is an atomic mobility which is positive.

To determine if the total grand potential is monotonically decreasing in time, we take the time derivative of the system's grand potential (Eq. 1)

$$\begin{aligned} \frac{d\Omega}{dt} &= \int_V \frac{\delta\Omega}{\delta\phi} \frac{\partial\phi}{\partial t} + \frac{\delta\Omega}{\delta\tilde{\mu}} \frac{\partial\tilde{\mu}}{\partial t} dV \\ &= \int_V \frac{\delta\Omega}{\delta\phi} \frac{\partial\phi}{\partial t} - c \frac{\partial\tilde{\mu}}{\partial t} dV \leq 0. \end{aligned} \quad (9)$$

For the grand potential to decrease in time requires the integrand to be negative-definite, which, when combined with Eq. 5, yields the condition

$$-M_\phi \left(\frac{\delta\Omega}{\delta\phi} \right)^2 - c \frac{\partial\tilde{\mu}}{\partial t} \leq 0. \quad (10)$$

For this to hold for any virtual variation in ϕ or $\tilde{\mu}$, each term must itself be negative. From Eq. 7, the second term can be written as $-c\partial_t\tilde{\mu} = -c\partial_t c/\chi$ for regions far from the boundary ($\partial_t\phi = 0$). Since the concentration is nonnegative $c \geq 0$, this necessitates c to monotonically increase/decrease with time for a positive/negative χ . However, this is not always the case, at least in a subdomain of the system. It is evident that the evolution equations of the grand-potential phase field model (Eqs. 5 and 7) do not minimize the total grand potential (Eq. 1). In other words, $d\Omega/dt$ is not guaranteed to be negative.

Thus, the model does not appear to guarantee that the grand potential energy decreases during evolution. However, as will be shown below, it dissipates the Helmholtz free energy. The Helmholtz free energy of the system is

$$F[\phi, c] = \int_V \frac{1}{2}\kappa|\vec{\nabla}\phi|^2 + mg(\phi) + f(\phi, c) dV, \quad (11)$$

where $f(\phi, c) = p(\phi)f^\alpha(c^\alpha) + (1 - p(\phi))f^\beta(c^\beta)$ is the Helmholtz free energy density, f^α and f^β are the Helmholtz free energy densities of each phase, which are related to the grand-potential densities as $\omega^\alpha = f^\alpha - c^\alpha\tilde{\mu}^\alpha$. Equation 11 can be reformulated using Eq. 1 as

$$F[\phi, c] = \Omega[\phi, \tilde{\mu}] + \int_V c\tilde{\mu} dV, \quad (12)$$

where the local equilibrium constraint $\tilde{\mu} = \tilde{\mu}^\alpha = \tilde{\mu}^\beta$ is imposed.

The evolution of the Helmholtz free energy requires

$$\frac{dF}{dt} = \frac{d\Omega}{dt} + \int_V \left(\frac{\partial c}{\partial t} \tilde{\mu} + c \frac{\partial\tilde{\mu}}{\partial t} \right) dV \quad (13)$$

$$= \int_V \frac{\delta\Omega}{\delta\phi} \frac{\partial\phi}{\partial t} + \tilde{\mu} \frac{\partial c}{\partial t} dV \quad (14)$$

$$= \int_V \frac{\delta\Omega}{\delta\phi} \frac{\partial\phi}{\partial t} + \vec{J} \cdot \vec{\nabla}\tilde{\mu} dV - \int_{\partial V} \hat{n} \cdot (\tilde{\mu}\vec{J}) dA \quad (15)$$

$$= \int_V -M_\phi \left(\frac{\delta F}{\delta\phi} \right)^2 - M|\vec{\nabla}\tilde{\mu}|^2 dV \leq 0, \quad (16)$$

where Eq. 9 is substituted into Eq. 13, and Eq. 6 is used in Eq. 14 with integration by parts. Equation 16 is obtained using the constitutive relations Eqs. 5 and 8, and the assumption that there is no mass flux across the boundary of V : $\hat{n} \cdot \vec{J} = 0$, where \hat{n} is the outward interfacial normal vector, and $\delta F/\delta\phi = \delta\Omega/\delta\phi$. Since M_ϕ and M are both positive, Eq. 16 shows the evolution equations in the grand-potential phase field model (Eqs. 5 and 6) minimizes the system's Helmholtz free energy (Eq. 11).

In deriving Eq. 16, we assume there is no mass flux at the boundary (closed system). For an open system that can exchange mass with the surroundings (or reservoir) at its boundary, a boundary integral is needed to account for this exchange process. The reservoir is assumed to be large compared to the system, so any exchange of mass

does not alter its diffusion potential $\tilde{\mu}_{\text{resv}}$. The proper quantity to be minimized for this open system is

$$L[\phi, c] = F[\phi, c] + \int_0^t \int_{\partial V} \hat{n} \cdot (\tilde{\mu}_{\text{resv}} \vec{J}) dA dt. \quad (17)$$

The time derivative of L can be worked out similarly as

$$\begin{aligned} \frac{dL}{dt} &= \int_V \frac{\delta F}{\delta \phi} \frac{\partial \phi}{\partial t} + \vec{J} \cdot \vec{\nabla} \tilde{\mu} dV \\ &\quad - \int_{\partial V} \hat{n} \cdot ((\tilde{\mu} - \tilde{\mu}_{\text{resv}}) \vec{J}) dA \end{aligned} \quad (18)$$

$$\begin{aligned} &= \int_V -M_\phi \left(\frac{\delta F}{\delta \phi} \right)^2 - M |\vec{\nabla} \tilde{\mu}|^2 dV \\ &\quad - \int_{\partial V} M_t (\tilde{\mu} - \tilde{\mu}_{\text{resv}})^2 dA \leq 0, \end{aligned} \quad (19)$$

where we use constitutive relations Eqs. 5 and 8 and boundary condition $\hat{n} \cdot \vec{J} = M_t (\tilde{\mu} - \tilde{\mu}_{\text{resv}})$, where M_t is a trans-interface atomic mobility that is positive. If atoms jump across the boundary fast ($M_t = +\infty$), we have $\tilde{\mu} = \tilde{\mu}_{\text{resv}}$ at the boundary, indicating that the system exchanges mass with the surroundings at a constant $\tilde{\mu}$. This means L is monotonically decreasing in time according to the evolution equations in Eqs. 5 and 7, while the grand potential Ω is not. At equilibrium, when mass diffusion has finished, the system has a uniform $\tilde{\mu}$ the same as the reservoir $\tilde{\mu} = \tilde{\mu}_{\text{resv}}$. L can be written as $L = F - \tilde{\mu}N + \tilde{\mu}_{\text{resv}}N_0 = \Omega + \text{constant}$, where N_0 and N are the total number of atoms in the system at $t = 0$ and after equilibrium, respectively. So, both L and Ω are at a minimum at equilibrium, which is consistent with classical thermodynamics.

Now, we consider a timescale that is much larger than the diffusion timescale. This means that diffusion happens so quickly that it appears that the system is connected to a mass reservoir everywhere, maintaining a constant $\tilde{\mu}$. As a result, we have $\tilde{\mu} = \tilde{\mu}_{\text{resv}}$ and $\vec{J} = -M \vec{\nabla} \tilde{\mu} = \vec{0}$ at all points in the system. For this open system that can exchange mass with the surroundings everywhere, the proper quantity to be minimized is

$$L^*[\phi, c] = F[\phi, c] + \int_0^t \int_V \tilde{\mu}_{\text{resv}} j dV dt, \quad (20)$$

where j is a body mass flux from the system to the surroundings (sink). The continuity equation, in this case, is $\partial c / \partial t = -j$, which can be substituted into Eq. 20 to give

$$\begin{aligned} L^*[\phi, c] &= F[\phi, c] - \int_V c \tilde{\mu} dV + \int_V c_0 \tilde{\mu}_{\text{resv}} dV \\ &= \Omega[\phi, \tilde{\mu}] + \tilde{\mu}_{\text{resv}} N_0. \end{aligned} \quad (21)$$

where c_0 is the concentration at $t = 0$. Note the last term in Eq. 21 is a constant. Therefore, L^* is equivalent to the grand potential Ω at all times, while L is equivalent to Ω only at equilibrium. It is critical to distinguish two cases:

(a) the system is only connected to the reservoir at the system's outer boundary (minimizing L), and (b) the system is connected to the reservoir at every point within the system or each subsystem is in contact with the reservoir (minimizing Ω). The first case can be handled by a boundary integral, as in Eq. 17, while the second case requires the Legendre transformation of the free energy *density*, as in Eq. 21.

In summary, in a closed system (no mass moving across its boundary), the Helmholtz free energy in Eq. 11 is dissipated (decreases monotonically) as the system evolves. In an open system where mass can be exchanged with the surroundings only through its boundary, L in Eq. 17 is minimized. For an open system that can exchange mass with the surroundings throughout the system to maintain an iso- $\tilde{\mu}$ condition, the grand potential in Eq. 1 or L^* in Eq. 20 is minimized. In all cases, the core quantity to be minimized is the Helmholtz free energy. The interaction with the surroundings is taken into account through various ‘boundary’ integrals, such as those in Eqs. 17 and 20. Here, ‘boundary’ refers to places where the system comes into contact with the reservoir. If we relax the isothermal assumption, the quantity to be minimized would be the negative entropy along with an appropriate boundary integral [22, 24]. This aligns with the equivalence of thermodynamic ensembles in statistical mechanics, which states that the boundary conditions determine the proper ensemble to employ.

Plapp’s grand-potential phase field model [3] was derived from the grand-potential functional in Eq. 1. Since we showed above that the Helmholtz free energy or L is the proper quantity to be minimized, we here provide an alternative derivation of Plapp’s model without utilizing the system’s grand potential. Considering a system with M phases and N components, the independent variables are the phase field vector $\phi = \{\phi_\alpha\}_{\alpha=1}^M$, and the concentration vector $c = \{c_i\}_{i=1}^{N-1}$. Assuming all species have the same molar volume V_m , we have $\sum_{i=1}^N c_i = 1/V_m$, so there are $N - 1$ independent concentrations. We choose the N -th component to define the diffusion potential $\tilde{\mu}_i = \mu_i - \mu_N$, where μ_i is the chemical potential of specie i .

The Helmholtz free energy of the system is

$$\begin{aligned} F[\phi, c] &= \int_V \sum_{\alpha=1}^M \frac{1}{2} \kappa |\vec{\nabla} \phi_\alpha|^2 + mg(\phi) \\ &\quad + \sum_{\alpha=1}^M p_\alpha(\phi) f^\alpha(c^\alpha(\tilde{\mu})) dV. \end{aligned} \quad (22)$$

where $g(\phi)$ is a multi-well potential [25], $p_\alpha(\phi)$ is the interpolation function of phase α for the multiple-phase case [26], $c^\alpha = \{c_i^\alpha\}_{i=1}^{N-1}$, and $\tilde{\mu} = \{\tilde{\mu}_i\}_{i=1}^{N-1}$. The key difference between our treatment and the KKS model (and its multiphase and multicomponent equivalent) is that we assume the phase concentrations c_i^α are a function of

the diffusion potentials $\tilde{\mu}_i^\alpha$, which are in turn a function of the independent variables ϕ and \mathbf{c} . This treatment allows us to directly impose the local equilibrium constraint $\tilde{\mu}_i = \tilde{\mu}_i^\alpha = \partial f^\alpha / \partial c_i^\alpha, \forall \alpha$.

The mixture rule for the phase concentrations is

$$c_i = \sum_{\alpha=1}^M p_\alpha(\phi) c_i^\alpha, \quad i = 1, \dots, N-1. \quad (23)$$

The functional derivatives of F to the independent field variables are derived using the chain rule and following the same procedure as in [5, 26]

$$\frac{\delta F}{\delta \phi_\alpha} = -\kappa \vec{\nabla}^2 \phi_\alpha + m \frac{\partial g(\phi)}{\partial \phi_\alpha} + \sum_{\beta=1}^M \frac{\partial p_\beta(\phi)}{\partial \phi_\alpha} \omega^\beta, \quad (24)$$

$$\frac{\delta F}{\delta c_i} = \tilde{\mu}_i. \quad (25)$$

The grand potential density ω in Eq. 24 arises naturally from the local equilibrium constraint and Eq. 23.

The evolution equations that minimize the system's Helmholtz free energy (Eq. 22) are (neglecting cross-coupling between ϕ and \mathbf{c})

$$\frac{\partial \phi_\alpha}{\partial t} = -M_\phi^\alpha \frac{\delta F}{\delta \phi_\alpha}, \quad (26)$$

$$\frac{\partial c_i}{\partial t} = \vec{\nabla} \cdot \left(\sum_{j=1}^{N-1} M_{ij} \vec{\nabla} \tilde{\mu}_j \right), \quad (27)$$

where M_ϕ^α are the phase field mobilities and M_{ij} are the atomic mobilities. At this point, we still need to solve the local equilibrium constraint $\tilde{\mu}_i = \tilde{\mu}_i^1 = \dots = \tilde{\mu}_i^M, i = 1, \dots, N-1$ at each grid point and time step to get the phase concentrations c_i^α . This problem can be resolved by reformulating the mass conservation equations (Eq. 27) using the diffusion potentials $\tilde{\mu}_i$, a critical step

in the original grand-potential phase field model [3], as

$$\chi_{ij} \frac{\partial \tilde{\mu}_j}{\partial t} = -\vec{\nabla} \cdot \left(\sum_{j=1}^{N-1} M_{ij} \vec{\nabla} \tilde{\mu}_j \right) - \sum_{\alpha=1}^M \left(\sum_{\beta=1}^M \frac{\partial p_\beta(\phi)}{\partial \phi_\alpha} c_i^\beta \right) \frac{\partial \phi_\alpha}{\partial t}, \quad (28)$$

where the susceptibility is $\chi_{ij} = \partial c_i / \partial \tilde{\mu}_j$.

The phase concentrations c_i^α can then be solved from the diffusion potentials $\tilde{\mu}_i$, and there is no need to explicitly impose the local equilibrium constraint like the KKS model. Equation 28 should not be viewed as the evolution of the independent field variables but as a reformulation of the mass conservation equations in Eq. 27. The independent field variables remain the concentrations since the Helmholtz free energy is minimized. Notably, when Eq. 28 is solved numerically, it can lead to an accumulated error in mass conservation, which requires careful treatment [9].

Conclusions. This work addresses an apparently widespread misapprehension regarding the grand-potential phase field model: What thermodynamic potential is minimized or dissipated during evolution? Although the original model's equations are correct, they do not result in a monotonically decreasing grand potential. Instead, the thermodynamic potential to be minimized is the Helmholtz free energy with the proper boundary condition. We identified a key difference between minimizing the Helmholtz free energy and the grand potential, which is related to how the system exchanges mass with the surroundings. When the system can only exchange mass with the surroundings through its outer boundary, the Helmholtz free energy (with boundary condition as boundary integral) decreases monotonically with time. On the other hand, if the system can exchange mass locally everywhere within the system, a finite diffusion rate is not present, and the grand potential is the proper quantity to be minimized. Although both quantities are at a minimum at equilibrium, they lead to different evolution equations, corresponding to physical processes at different timescales.

Acknowledgments. We acknowledge the financial assistance award 70NANB14H012 from the U.S. Department of Commerce, National Institute of Standards and Technology as part of the Center for Hierarchical Materials Design (CHiMaD). We would like to thank Professor Mathis Plapp for his valuable comments.

[1] A. A. Wheeler, W. J. Böttlinger, and G. B. McFadden, Phase-field model for isothermal phase transitions in bi-

nary alloys, [Physical Review A 45, 7424 \(1992\)](#).

- [2] S. G. Kim, W. T. Kim, and T. Suzuki, Phase-field model for binary alloys, *Physical Review E* **60**, 7186 (1999).
- [3] M. Plapp, Unified derivation of phase-field models for alloy solidification from a grand-potential functional, *Physical Review E* **84**, 031601 (2011).
- [4] A. Choudhury and B. Nestler, Grand-potential formulation for multicomponent phase transformations combined with thin-interface asymptotics of the double-obstacle potential, *Physical Review E* **85**, 021602 (2012).
- [5] L. K. Aagesen, Y. Gao, D. Schwen, and K. Ahmed, Grand-potential-based phase-field model for multiple phases, grains, and chemical components, *Physical Review E* **98**, 023309 (2018).
- [6] D. A. Cogswell, Quantitative phase-field modeling of dendritic electrodeposition, *Physical Review E* **92**, 011301 (2015).
- [7] J. Zhang, A. F. Chadwick, and P. W. Voorhees, Quantitative phase field model for electrochemical systems, *Journal of The Electrochemical Society* **170**, 120503 (2023).
- [8] P. Kubendran Amos and B. Nestler, Grand-potential based phase-field model for systems with interstitial sites, *Scientific reports* **10**, 22423 (2020).
- [9] S. Khanna, S. K. Aramanda, and A. Choudhury, Role of solid–solid interfacial energy anisotropy in the formation of broken lamellar structures in eutectic systems, *Metallurgical and Materials Transactions A* **51**, 6327 (2020).
- [10] S. Chatterjee and N. Moelans, A grand-potential based phase-field approach for simulating growth of intermetallic phases in multicomponent alloy systems, *Acta Materialia* **206**, 116630 (2021).
- [11] C. Xuan and W. Mu, New insights of heterogeneous nucleation and anisotropic growth of acicular ferrite on non-metallic inclusion, *Materials & Design* **221**, 110892 (2022).
- [12] M. Sessim, L. Shi, S. R. Phillpot, and M. R. Tonks, Phase-field modeling of carbon fiber oxidation coupled with heat conduction, *Computational Materials Science* **204**, 111156 (2022).
- [13] T. Boutin, W. Verdier, and A. Cartalade, Grand-potential-based phase-field model of dissolution/precipitation: Lattice boltzmann simulations of counter term effect on porous medium, *Computational Materials Science* **207**, 111261 (2022).
- [14] A. Mamaev and N. Provatas, Analysis of the self-consistency of nucleation in the diffuse interface limit of binary alloy phase field models, *Physica Scripta* **99**, 015948 (2023).
- [15] M. Xue and M. Yi, Phase-field simulation of sintering process: A review., *CMES-Computer Modeling in Engineering & Sciences* **140**, 10.32604/cmes.2024.049367 (2024).
- [16] M. A. Muntaha, S. Chatterjee, S. Blondel, L. Aagesen, D. Andersson, B. D. Wirth, and M. R. Tonks, Impact of grain boundary and surface diffusion on predicted fission gas bubble behavior and release in UO₂ fuel, *Journal of Nuclear Materials* **594**, 155032 (2024).
- [17] R. Bayle, O. Cueto, S. Blonkowski, T. Philippe, H. Henry, and M. Plapp, Phase-field modeling of the non-congruent crystallization of a ternary Ge–Sb–Te alloy for phase-change memory applications, *Journal of Applied Physics* **128**, 10.1063/5.0023692 (2020).
- [18] W. Verdier, A. Cartalade, and M. Plapp, Grand-potential phase field simulations of droplet growth and sedimentation in a two-phase ternary fluid, *Modelling and Simulation in Materials Science and Engineering* 10.1088/1361-651x/ad627e (2024).
- [19] D. A. Danilov, V. G. Lebedev, and P. K. Galenko, A grand potential approach to phase-field modeling of rapid solidification, *Journal of Non-Equilibrium Thermodynamics* **39**, 93 (2014).
- [20] S. Chatterjee, D. Schwen, and N. Moelans, A computationally efficient and mechanically compatible multi-phase-field model applied to coherently stressed three-phase solids, *Computational Materials Science* **218**, 111969 (2023).
- [21] J. S. Langer, Models of pattern formation in first-order phase transitions, in *Directions in Condensed Matter Physics* (World Scientific, 1986) pp. 165–186.
- [22] O. Penrose and P. C. Fife, Thermodynamically consistent models of phase-field type for the kinetic of phase transitions, *Physica D: Nonlinear Phenomena* **43**, 44 (1990).
- [23] R. P. Feynman, *Statistical mechanics: a set of lectures* (CRC press, 2018).
- [24] R. F. Sekerka, Irreversible thermodynamic basis of phase field models, *Philosophical Magazine* **91**, 3 (2011).
- [25] D. Fan and L.-Q. Chen, Computer simulation of grain growth using a continuum field model, *Acta Materialia* **45**, 611 (1997).
- [26] N. Moelans, A quantitative and thermodynamically consistent phase-field interpolation function for multi-phase systems, *Acta Materialia* **59**, 1077 (2011).